



Your card has what?! [click here to apply online](#)

0% Intro APR No Annual Fee
Free Balance Transfers

AMERICAN EXPRESS Cards

IBM Intellectual Property Network

[IPN Home](#) [Search](#) [Order Form](#) [Feedback](#) [Help](#)



JP6192874A: REFINING METHOD FOR COBALT

[View Images \(1 pages\)](#)

Inventor(s): SHINDO YUICHIRO
Applicant(s): JAPAN ENERGY CORP
Issued/Filed Dates: July 12, 1994 / Dec. 24, 1992
Application Number: JP1992000357367
IPC Class: C25C 001/08; C22C 019/07;

Abstract: **Purpose:** To obtain an extremely high purity cobalt suitable for applications such as a target or the like.
Constitution: The purified cobalt is electrolytically refined by electrodepositing on a cathode plate by using a crude cobalt as an anode and a cobalt sulfate aq. solution as an electrolyte in the electrolysis condition of pH 1-3, 40-160g/l cobalt content and 0.001-0.1A/cm² current density. Nickel or iron content in the electrodeposited cobalt is reduced to 1ppm, particularly 0.5ppm. The average conc. of nickel and iron in the cobalt sulfate aq. solution are respectively controlled to preferably 1.3mg/l and 0.1mg/l.
COPYRIGHT: (C)1994,JPO&Japio

Foreign References: none

(No patents reference this one)



[Nominate this invention for the Gallery...](#)

Alternate Searches

[Patent Number](#)

[Boolean Text](#)

[Advanced Text](#)

PatentMiner

SEARCH PATENT FULL TEXT
WITH NATURAL LANGUAGE